

Resistant Alloys

Copper-Nickel Alloys



1. Chemical composition

	Ni	Cu	Fe	Mn	Others
%	63 min.	28 - 34	2.5 max	2.0 max	

2. Physical properties

- Resistivity (Ω mm ² /m)	: 0.547
- Temperature coefficient (K x 10 ⁻⁶ /°C) from 20 to 100 °C	:
- Thermal conductivity at 120 °C (Wm ⁻¹ °C ⁻¹)	: 21.8
- Coefficient of linear expansion (coeff. 10 ⁻⁶ /°C) from 20 to 100 °C	: 13.90
- Density (g/cm ³)	: 8.90
- Melting point (°C)	: 1 350
- Maximal operating temperature (°C)	:

Standard mechanical properties

- Tensile Strength (daN/mm ²)	: 50
- Yield Strength (daN/mm ²)	: 35
- Elongation (A% on 100 mm)	: 25
- Hardness (HV)	: 120

3. Typical Applications

This nickel-copper alloy presents a good ductibility, a high resistance and an excellent resistance to corrosion in a wide variety of environment including seawater, hydrofluoric water, sulfuric acid and alkalis.

Sept 2020 - The data enclosed in this document are only given as indicative values and correspond to our standard products. Different specific requirements are subject to discussion and formal approval by Aperam Alloys Rescal. For further information or special request, please contact us.