



aperam

**Our stainless steel solutions:  
the most complete range available on the market**

# Surface aspects


Standard finishes with the most innovative appearances, available from our service centres and mills.

Conditions	Designation Stainless Europe	Description of surface finish	International equivalents	
			ASTM	EN 10088
HR	HRAP	Hot-rolled, annealed and pickled	N°1	1D
	DIN embossed	Hot-rolled with embossed DIN tear-plate pattern, annealed and pickled		1M
	ASTM embossed	Hot-rolled with embossed ASTM tear-plate pattern, annealed and pickled	pattern B	
CR annealed	HRC	Cold-rolled, rough, matt		2E
	2D	Cold-rolled, annealed and pickled, not skinpassed	2D	2D
	2B	Cold-rolled, annealed, pickled and skinpassed	2B	2B
	2R	Cold-rolled, bright-annealed and skinpassed	BA	2R
CR work hardened	Work hardened <sup>(6)</sup>	Cold-rolled without subsequent anneal for various hardness levels	TR	2H
CR annealed	N°3 or P80D	No. 3 polished / Dry polished with 80-grit abrasive belts	N°3	2G
	N°4 or P120D-P150D	No. 4 polished / Dry polished with 120/150-grit abrasive belts	N°4	2G
	N°5 or P180D-P220D	No. 5 polished / Dry polished with 180/220-grit abrasive belts		2G
	N°6 or P240D	No. 6 polished / Dry polished with 240-grit abrasive belts		2G
	N°7 or P320D	No. 7 polished / Dry polished with 320-grit abrasive belts		2G
	P400D	Dry polished with 400-grit abrasive belts		2G
	Duplo P220	Dry polished with 220-grit abrasive belts + brushed with wire rolls		2G
	Duplo P320	Dry polished with 320-grit abrasive belts + brushed with wire rolls		2G
	Uginox Rolled-On	240-grit polish look like obtained by rolled-on process		2J
	Scotch-Brite	Lightly brushed with wire rolls		2J
CR annealed	Uginox Linen	Etched linen finish obtained by cold rolling with special rolls, followed by a final anneal		2M
	Uginox Squares	Etched chequer patterned finish obtained by cold rolling with special rolls, followed by a final anneal		2M
	Uginox Lozenge	Etched lozenge patterned finish obtained by cold rolling with special rolls, followed by a final anneal		2M
	Uginox Sand	Finish obtained by etching with special rolls	-	-
	Uginox Access	Matt finish obtained by cold rolling with special rolls	2D	2D
	Uginox Bright	2R finish for construction industry	BA	2R
	Uginox Mat	2B finish for construction industry	2B	2B
	Uginox Top	Matt low-reflectance finish obtained by cold rolling with special rolls	2D	2F
	Uginox Patina	Surface coated with a continuous layer of tin in accordance with standard NFA 36332		2S
CR work hardened	Uginox Leather	Etched textured finish obtained by cold rolling with special rolls		2M

This table does not take into account the availability of grades or dimensional restrictions.  
 > Check with your sales contact.


<sup>(6)</sup> Special finishes possible - consult us.

# Our grades

	Grade designations	Standards			Chemical composition (typical values)						
		AISI	UNS	EN	C	Si	Mn	Cr	Mo	Ni	Others
<b>Ferritic stainless steels</b> 	K03 (F12N)		S41003	1.4003	0.020	0.50	0.60	11.00		0.40	
	K09 (F12T)	409	S40900	1.4512	0.010	0.45	0.30	11.30			Ti = 0.190
	K09D (F12TD)	409	S40900	1.4512	0.010	0.45	0.30	11.30			Ti = 0.190
	K09X (F12T)	409	S40900	1.4512	0.010	0.45	0.30	11.30			Ti = 0.190 - N = 0.010
	K30 (F17)	430	S43000	1.4016	0.040	0.35	0.30	16.50			
	K30ED (F17)	430	S43000	1.4016	0.015	0.35	0.40	16.50			
	K30H (F17)	430	S43000	1.4016	0.070	0.45	0.40	16.20			
	K33X (FNT)	433	S43690	1.4513	0.015	0.50	0.25	17.30	0.90		N = 0.015 - Ti = 0.35
	K36 (F17MnNb)	436	S43600	1.4526	0.020	0.40	0.25	17.50	1.25		Nb = 0.50
	K36X (F17MnNb)	436	S43600	1.4526	0.020	0.40	0.25	17.50	1.25		N = 0.015 - Nb = 0.50
	K39 (F18T)	439	S43035	1.4510	0.020	0.40	0.30	17.50			Ti = 0.35
	K39M (F17T)	430Ti	S43037	1.4510	0.020	0.40	0.30	16.50			Ti = 0.40
	K41 (F18TNb)	441 <sup>(1)</sup>	S43932/S43940	1.4509	0.015	0.60	0.30	17.80			Ti + Nb = 0.65
	K41X (F18TNb)	441 <sup>(1)</sup>	S43932	1.4509	0.015	0.60	0.30	17.80			N = 0.015 - Ti + Nb = 0.65
	K44 (F18MT)	444	S44400	1.4521	0.015	0.50	0.30	17.70	1.85		Ti + Nb = 0.45
	K44M (F19MnNb)	444	S44400	1.4521	0.015	0.40	0.30	19.00	1.90		N = 0.015 - Nb = 0.60
K44X (F19MnNb)	444	S44400	1.4521	0.015	0.40	0.30	19.00	1.90		N = 0.015 - Nb = 0.60	
K45 (F20NbCu)	445 <sup>(1)</sup>	S44500	1.4621	0.015	0.25	0.25	20.20			Nb = 0.45 - Cu = 0.45	
<b>Austenitic stainless steels containing manganese</b>	Aperam 201 (16-4Mn)	201	S20100	1.4372	0.090	0.50	6.50	16.30		4.15	
	Aperam 201D (17-4Mn)	201-1	S20100	1.4618	0.050	0.35	6.00	16.80		4.60	N = 0.10 - Cu = 1.6 - S ≤ 0.002
	Aperam 201LN (16-5MnL)	201LN	S20153	1.4371	0.025	0.50	7.00	16.30		4.75	N = 0.18 - Cu = 0.30
<b>Duplex</b>	DX1803	22-05	S31803	1.4462	0.020	0.30	1.80	22.10	2.70	5.10	N = 0.17
	DX2202	22-02	S32202	1.4062	0.025	0.40	1.30	23.00	0.30	2.50	N = 0.21
	DX2205	22-05	S32205	1.4462	0.020	0.30	1.80	22.80	3.10	5.50	N = 0.17
	DX2304	23-04	S32304	1.4362	0.020	0.40	1.50	23.00	0.30	4.90	Cu = 0.40 - N = 0.10
<b>Austenitic stainless steels</b>	Aperam 301 (17-7A)	301	S30100	1.4310	0.100	0.90	1.30	16.80		6.60	
	Aperam 301L (18-7L)	301L/301LN	S30103/S30153	1.4318	0.025	0.50	1.70	17.50		6.60	N = 0.110
	Aperam 301M (17-7C)	301	S30100	1.4310	0.100	0.60	0.90	17.30		7.30	
	Aperam 301R (17-7E)	(301)	S30100	1.4310	0.100	1.15	1.20	16.70	0.70	6.65	
	Aperam 304 (18-9E)	304	S30400	1.4301	0.050	0.40	1.10	18.20		8.05	
	Aperam 304D (18-9ED)	304	S30400	1.4301	0.040	0.40	1.20	18.20		8.10	
	Aperam 304ED (18-9DDQ)	304	S30400	1.4301	0.045	0.40	1.10	18.20		9.10	
	Aperam 304H (18-9H)	304H	S30409	1.4301/1.4948	0.050	0.40	1.10	18.20		8.05	C mini 0.04
	Aperam 304L (18-9L)	304L	S30403	1.4307	0.025	0.40	1.40	18.20		8.05	
	Aperam 304M (18-10L)	304L	S30403	1.4306	0.025	0.40	1.30	18.20		10.10	
	Aperam 305 (18-12D)	305	S30500	1.4303	0.025	0.40	1.30	18.50		12.60	
	Aperam 321 (18-10T)	321	S32100	1.4541	0.025	0.40	1.10	17.15		9.10	Ti = 0.30
Aperam 321H (18-10TH)	321H	S32109	1.4541/1.4878	0.045	0.40	1.10	17.15		9.10	Ti = 0.30	
<b>Austenitic stainless steels containing molybdenum</b>	Aperam 316B (18-13MS)	316L	S31603	1.4435	0.020	0.40	1.35	17.30	2.60	12.70	
	Aperam 316C (18-12MS)	316L	S31603	1.4432	≤0.03	0.40	1.35	16.80	2.60	11.10	
	Aperam 316L (18-11ML)	316/316L	S31600/S31603	1.4401/1.4404	0.025	0.40	1.20	18.20	2.10	10.10	
	Aperam 316T (17-11MT)	316Ti	S31635	1.4571	0.035	0.40	1.20	16.80	2.10	10.70	Ti = 0.350
<b>Heat resisting stainless steels</b>	Aperam 309 (R20-12)			1.4828	0.050	1.60	1.35	19.30		11.40	
	Aperam 309S (R24-13S) <sup>(2)</sup>	309S / 309H	S30908	1.4833	0.060	0.40	1.30	22.20		13.60	
<b>Martensitic stainless steels</b>	Aperam MA2			1.4021	0.220	0.35	0.35	13.30			
	Aperam MA3	420	S42000	1.4028	0.320	0.35	0.30	13.70			
	Aperam MA3M			1.4419	0.380	0.30	0.30	14.00	0.80		
	Aperam MA4			1.4034	0.460	0.40	0.30	13.80			
	Aperam MA5				0.350	0.35	0.35	16.00			N = 0.15



# Size range

	Size range		
	Surface condition and appearance	Thickness in mm	Width in mm
<b>Ferritic stainless steels</b> 	HRAP	1.50 - 2.49	1 000
		2.50 - 2.99	1 250
		3.00 - 6.50	1 524
	2B - 2D	0.40 - 0.59	1 250
		0.60 - 4.00	1 524
	2R	0.30 - 0.39	1 000
		0.40 - 0.69	1 250
		0.70 - 2.00	1 500
<b>Austenitic stainless steels</b> containing manganese	HRAP	2.00 - 2.50	1 000
		2.50 - 3.50	1 250
		3.50 - 5.00	1 500
		5.00 - 13.00	2 000
	HRC	4.00 - 4.99	2 000
	2D - 2B	0.60 - 2.80	1 250
		0.80 - 1.00 <sup>(5)</sup>	1 500
		1.00 - 8.00	2 000
<b>Duplex</b>	HRAP	4.00 - 10.00	1 500
		7.00 - 10.00	2 000
	2B - 2E	1.00 - 6.00	1 500
		2.00 - 6.00	2 000
<b>Austenitic stainless steels</b>	HRAP	1.85 - 2.49	1 000
		2.50 - 2.99	1 250
		3.00 - 4.99	1 524
		5.00 - 13.00	2 000
		4.00 - 4.99	2 000
	HRC	0.40 - 0.59	1 250
		0.60 - 0.79	1 500
		0.80 - 0.99	1 524
		1.00 - 8.00	2 000
	2B - 2D	0.30 - 0.39	1 000
		0.40 - 0.79	1 250
		0.80 - 2.00	1 524
2R	0.30 - 0.39	1 000	
	0.40 - 0.79	1 250	
		0.80 - 2.00	1 524
<b>Austenitic stainless steels</b> containing molybdenum	HRAP	2.50 - 2.99	1 000
		3.00 - 4.39	1 250
		4.40 - 6.99	1 524
		7.00 - 13.00	2 000
	HRC	3.00 - 4.39	1 524
		4.00 - 6.99	2 000
	2B - 2D	0.40 - 0.79	1 250
		0.80 - 1.49	1 524
		1.50 - 8.00	2 000
		0.30 - 0.39	1 000
2R	0.40 - 2.00	1 250	
			3.50 - 7.99
<b>Heat resisting stainless steels</b>	HRAP	8.00 - 13.00	2 000
		0.40 - 0.79	1 250
	2D - 2B	0.80 - 1.49	1 250
		1.50 - 8.00	2 000
<b>Martensitic stainless steels</b>	2B - 2H	0.40 - 3.50	1 000

**A unique offer:**  
from 0.3 to 13 mm thick and up to 2 m wide.

<sup>(5)</sup> Consult us for thicker than 1.0 mm.  
For precise information on specific grades and surface finishes:  
consult your correspondent.

Strip - Coil		
Supply possibilities according to thickness and width in the annealed condition*		
Thickness in mm	Min. width in mm	Max. width in mm
0.3 ≤ t < 0.4	8	1 000
0.4 ≤ t < 0.7	8	1 250
0.8	10	1 524
1.0	10	1 524
1.5	10	2 000
2.0	10	2 000
2.5	10	2 000
4.0	15	2 000
8.0	20	2 000
10.0	30	2 000
12.0	40	2 000
13.0	40	2 000

\* 2B - 2D - 2E - 2H - 2R (excluding HRAP)

Discs (Press blanked discs)		
Around 200 diameters are available		
Thickness in mm	Minimal diameter in mm	Maximum diameter in mm
0.37 ≤ t ≤ 2.50	80	704

Please consult us for other dimensions (between Ø 704 mm and Ø 1500 mm and/or thicknesses between 2.50 mm and 5 mm)

Blank - Sheet - Plate		
Thickness according to width		
Thickness in mm	Min. width in mm	Max. width in mm
0.30 - 0.74	80	1 250
0.75 - 2.00	80	1 524
2.01 - 8.00 LAF	670	2 000
3.00 - 13.00 LAC	500	2 000

Length: min. 275 mm/max. 16,000 mm

# Committed to your project's success

To ensure your project's success, we offer you a solution tailored to your exact requirements and with the properties you need. This commitment includes:

- > Ongoing support, solutions tailored to each market, expert advice on choosing of the right grade, responsive technical assistance, logistical offers and pooled expertise to work on joint development projects,
- > The most complete and innovative range on the market,
- > Specialities: ferritic and bright annealed stainless steels, proven hot-rolled quality and strip width of up to 2,000 mm.

## Contacts

### Flat Products

#### Austria

**Aperam**  
Services & Solutions Austria  
Traunfurterstr. 110a  
A - 4052 Ansfelden  
T +43 7229 8292 0  
F +43 7229 8292 013

#### Benelux

**Aperam**  
Services & Solutions Belgium  
Bosdel 87 - Genk Zuid - zone 5  
BE - 3600 Genk  
T +32 89 36 56 00  
F +32 89 36 56 02

#### Czech Republic & Slovakia

**Aperam**  
Services & Solutions Czech  
Republic Slezská 13  
CZ - 120 00 Praha 2  
T +420 2 210 01 602  
F +420 2 210 01 605

#### France

**Aperam**  
Services & Solutions France  
Rue Pierre Loti  
FR - 62330 Isbergues  
T +33 3 21 63 58 00  
F +33 3 21 63 58 59

#### Germany

**Aperam**  
Services & Solutions Germany  
Hildener Straße 28  
DE - 40699 Erkrath  
T +49 2104 309 0  
F +49 2104 309 243

#### Hungary

**Aperam**  
Services & Solutions Hungary  
Varosmajor u. 13.  
HU - 1122 Budapest  
T +36 122 52 480  
F +36 122 52 481

#### Italy

**Aperam**  
Località Priora, 4  
26815 Massalengo (LO) Italia  
T +39 0371 490 410  
F +39 0371 490 440

#### Luxembourg

**Aperam**  
Stainless Services & Solutions  
Luxembourg  
15, Avenue de l'Europe, site du PED L  
4830 Rodange  
T +352 50 54 81 1

#### Poland

**Aperam**  
Services & Solutions Poland  
ul. Henryka Krupanka 97  
PL - 41-103 Siemianowice Slaskie  
T +48 32 76 36 121/122/123  
F +48 32 76 36 139

#### Scandinavia

**Aperam**  
Services & Solutions Nordic AB  
Sigurdsgatan 21, 8th floor  
SE-721 30 Västerås - SWEDEN  
T +46 16 15 85 00  
F +46 16 15 85 19

#### Spain/Portugal

**Aperam**  
Services & Solutions Iberica  
Pol. Ind. Can Calderon  
C/Torrent Fondo, 7  
ES - 08840 Viladecans  
T +34 93 425 97 00  
F +34 93 425 97 33

#### Switzerland

**Aperam**  
Services & Solutions Switzerland  
Industriestrasse 19  
CH - 8112 Otelfingen  
T +41 44 851 56 56  
F +41 44 851 56 57

#### United Kingdom

**Aperam**  
Services & Solutions UK  
9 Midland Way - Barlborough  
GB - Chesterfield - S43 4XA  
T +44 1246 5716 60  
F +44 1246 5716 61

#### Canada

**Aperam**  
Services & Solutions Canada  
1005 Skyview Drive, Suite 100  
Burlington, Ontario, L7P 5B1  
T +1289 313 2000  
F +1905 336 0419

#### United States

**Aperam**  
Services & Solutions USA  
98 Floral avenue  
New Providence, NJ07974  
T +1908 988 0625  
F +1908 988 0664

#### For export other countries

**Aperam Stainless Europe**  
Immeuble «Le Cézanne»  
6 rue Henri Campra  
FR - 93210 La Plaine Saint-Denis  
Cedex - France  
T +33 1 71 92 06 99  
F +33 1 71 92 07 96

-  Head office
-  Sales office
-  Service Centre & Sales office
-  Plant
-  Research Centre



[www.aperam.com](http://www.aperam.com)  
contact@aperam.com

